



Technical Data: Office

Basis weight	g/m ²	ISO 536		80 ± 3.0
Caliper	µm	ISO 534	min	100
Opacity	%	ISO 2471		92.0 ± 1
Moisture abs.	%	ISO 287		4.6 ± .6
Brightness UV	%	ISO 2470		104.0 ± 1.5
CIE Whiteness	%	ISO 11475		146 ± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and ISO 45001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

This specification is valid for one year after issue or good till cancelled.